



TDS 9.2
WARRIOR WOODTREAT WOODSEAL EXTERIOR

DESCRIPTION:

Warrior Woodtreat Woodseal Exterior is a high quality sealer which penetrates the wood grain and nourishes the wood thus enhancing its natural beauty. It is specially formulated to protect wood against fungal attack and the harsh UV radiation of the sun. Warrior Woodtreat Woodseal Exterior does not peel or flake off on ageing and therefore overcoating is simplified.

Warrior Woodtreat Woodseal Exterior is available in tinted colours or clear (transparent) gloss finish.

USES:

Warrior Woodtreat Woodseal Exterior is ideal for use on wooden garage doors, window frames, garden furniture, gates, fascia, pergolas, panelling etc.

SPECIFICATION OR RECOMMENDED PAINT SYSTEM:

SURFACE PREPARATION:

New Wood Surfaces: All surfaces must be sanded to a smooth surface, cleaned and dry.

Previously Treated Wood Surfaces: All painted or varnished surfaces must be stripped chemically or mechanically back to the bare wood. Sand bare wood to a smooth finish and ensure the surface is clean, firm and dry. Apply Warrior Woodtreat Woodseal.

Previously Treated Wood Surfaces with Warrior Woodtreat Woodseal: Ensure the surface is sound, clean, firm and dry. Apply Warrior Woodtreat Woodseal.

RECOMMENDED APPLICATION:

Always stir Warrior Woodtreat Woodseal Exterior thoroughly before use. In addition stir regularly during application. On new wood it is recommended that 3 coats be applied unthinned and allow 24 hours to dry between coats. On wood previously treated with Woodtreat Woodseal apply 2 coats unthinned allowing 24 hours to dry between coats. It is important to sand the sealer lightly with a fine sand paper between coats for a good finish.

PROPERTIES:

APPLICATION:	Brush only
CLEANING SOLVENT:	Mineral Turps
THINNING SOLVENT:	Not recommended
SPREADING RATE:	PRIMER COAT: 9-10m ² per litre FINAL COAT: 11-12 m ² per litre
DRYING TIMES:	SURFACE DRY: 4-6 hours HARD DRY: 24 hours OVERCOATING: 24 hours
PACK SIZE:	1L, 5L
COLOUR RANGE:	Clear, Meranti, Mahogany, Oak, Teak and Imbuia
SPECIFIC GRAVITY:	0,90 ± 0,05 kg per litre
VISCOSITY:	30-40 "F4
FLASH POINT:	>35°C
FINISH:	Gloss



GENERAL INFORMATION:

- a) Not recommended for spraying and has limited abrasion resistance.
- b) A minimum of 3 coats must be applied to achieve a full gloss finish.
- c) It is important that this product be thoroughly mixed with a flat paddle before use.
- d) As per standard painting practices, no painting should take place if surface or ambient temperatures are below 10°C or above 30°C. Painting should cease at 3pm or when rain is imminent.

DISCLAIMER

The recommendations contained herein are given in good faith and are meant as a guide for specifiers and users. They are based on laboratory tests and practical historical experience. No guarantee or warranty is implied by the recommendations contained in the Technical Data Sheet as conditions of use, application method, cleanliness and soundness of the substrate are beyond our control.

N.B. Technology may change with time necessitating changes to the Technical Data Sheet (TDS). It is the specifiers and users responsibility to ascertain that the latest TDS is being used.

WARRIOR PAINTS AND COATINGS (PTY) LTD (REG NO. 1987/003946/07)
45 FRANS DU TOIT STREET
P O BOX 911-1181
ROSSLYN 0200
SOUTH AFRICA

HELP DESK
EMAIL: info@warriorpaints.co.za
TEL: +27 12 5413596
FAX: +27 12 541 1434
www.warriorpaints.co.za