



TDS 9.5
WARRIOR WOODTREAT YACHT VARNISH

DESCRIPTION:

Warrior Woodtreat Yacht Varnish is a clear gloss varnish with excellent resistance to wet and humid conditions and the ultra-violet radiation of the sun.

USES:

Warrior Woodtreat Yacht Varnish is ideal for use on yacht decks, railings, cabins, etc. It is also ideal for use on gates, doors, garden furniture, pergolas, fascia, weather boarding etc.

SPECIFICATION OR RECOMMENDED PAINT SYSTEM:

SURFACE PREPARATION:

New Wood Surfaces: All surfaces must be sanded to a smooth surface, cleaned and dry.

Previously Varnished Wood Surfaces in good condition: Sand to a smooth finish to create a good key. Wipe with a damp cloth and allow to dry.

Previously Varnished Wood Surfaces in poor condition: All painted or varnished surfaces must be stripped chemically or mechanically back to the bare wood. Sand the bare wood to a smooth finish and ensure surface is clean, firm and dry.

RECOMMENDED APPLICATION:

Always stir Woodtreat Yacht Varnish thoroughly before use. In addition stir regularly during application. It is recommended that on new wood the 1st coat be thinned 10-15% by volume with Warrior Mineral Turps. Apply a further 2 coats unthinned to complete the coating system. For previously varnished wood apply 2 maintenance coats unthinned. Allow at least 24 hours drying time between coats. It is important to sand the varnish lightly with a fine sand paper between coats for a good finish.

PROPERTIES:

APPLICATION:	Brush / Roller / Spray
CLEANING SOLVENT:	Mineral Turps
THINNING SOLVENT:	Mineral Turps
SPREADING RATE:	PRIMER COAT: 9m ² per litre FINAL COAT: 10-11 m ² per litre
DRYING TIMES:	SURFACE DRY: 4 hours TOUCH DRY: 24 hours OVERCOATING: 24 hours
PACK SIZE:	1L, 5L
COLOUR RANGE:	Clear & tinted colours (Mahogany, Light Oak, Dark Oak, Teak, Meranti Imbuia and Ebony)
SPECIFIC GRAVITY:	0,90 ± 0,05 kg per litre
VISCOSITY:	70-75KU
FLASH POINT:	>35°C
FINISH:	Gloss



GENERAL INFORMATION:

- a) It is recommended that a minimum of 3 coats be applied for a more durable finish.
- b) It is important that this product be thoroughly mixed with a flat paddle before use.
- c) As per standard painting practices, no painting should take place if surface or ambient temperatures are below 10°C or above 30°C. Painting should cease at 3pm or when rain is imminent.

DISCLAIMER

The recommendations contained herein are given in good faith and are meant as a guide for specifiers and users. They are based on laboratory tests and practical historical experience. No guarantee or warranty is implied by the recommendations contained in the Technical Data Sheet as conditions of use, application method, cleanliness and soundness of the substrate are beyond our control.

N.B. Technology may change with time necessitating changes to the Technical Data Sheet (TDS). It is the specifiers and users responsibility to ascertain that the latest TDS is being used.

WARRIOR PAINTS AND COATINGS (PTY) LTD (REG NO. 1987/003946/07)
45 FRANS DU TOIT STREET
P O BOX 911-1181
ROSSLYN 0200
SOUTH AFRICA

HELP DESK
EMAIL: info@warriorpaints.co.za
TEL: +27 12 5413596
FAX: +27 12 541 1434
www.warriorpaints.co.za